



CEWELD SG Corten Tig

TYPE Copper coated welding wire developed for TIG welding of weather resistant steels.

ANWENDUNGEN Weather resistant steels, art constructions, bridges, ovens, deco parts etc.

EIGENSCHAFTEN Due to the addition of 0,5% copper and 0,8% Ni this alloy offers excellent weather resistant properties

KLASSIFIKATION

AWS	A 5.28: ER 80S-G
EN ISO	636-A: W 42 4 Z2NiCu
F-nr	6
FM	1

GEEIGNET FÜR **CuNi, Reh ≤ 460MPa Iso 15608: 1.4**
 1.8963, 1.8946, 1.8965
 S235JRG2Cu, S235J2G4Cu, S235J0Cu, S235JRW, S355J0Cu, S355J2G3Cu, S355J0W, 235J2W-
 S355J2W, S355K2W, WTSt 37, WTSt 52,
 ASTM A 588M Grade A,B, C...K, A 618 Gr. II; A 709 Gr. 50 WF3
 CORten A, B, C, Patinax 37

ZULASSUNGEN CE

SCHWEISSPOSITIONEN

TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	P	S	Ni	Cu
0.08	0.6	1.3	0.015	0.015	0.8	0.4

MECHANISCHE GÜTEWERTE

Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
				-40°C		
As Welded	460	570	22	55		HRc

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175 I1



CEWELD SG Corten Tig

SG CORTEN TIG 1,6 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663406279

SG CORTEN TIG 2,0 X
1000MM

Packaging	KG/unit	EanCode
Tube	2,5	8720663406286

SG CORTEN TIG 2,4 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663406293

SG CORTEN TIG 3,2 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663406309