



CEWELD AA M CrMo1

TYPE Seamless metal core wire without slag with M21, for heat and creep resistant applications

ANWENDUNGEN Construction of containers, boilers, machines and pipe work. Construction of steam boilers and steam turbines.

EIGENSCHAFTEN Good arc restriking even with cold wire tip, suitable for robot applications. Ideal for use in the field short arc and spray arc. Excellent gap bridging for root welding. High-efficiency type for economic production environments and CrMo-steels up to 550 °C (1022°F) . Due to the seamless production process the hydrogen content is below 3ml/100gr weld metal even after long storage in unconditioned condition.

KLASSIFIKATION

AWS	A 5.28: E80C-B2 H4
EN ISO	17634-A: T CrMo1 M M21 1 H5
F-nr	6
FM	3

GEEIGNET FÜR **Typ 1Cr0,5Mo, ISO 15608: ~5,1**
 1.7335, 1.7262, 1.7728, 1.7218, 1.7225, 1.7258, 1.7354, 1.7357, 1.7205, 1.7218, 1.7225, 1.7228, 1.7254, 1.7262, 1.7335, 1.7337, 1.7350, 1.7354, 1.7357, 13CrMoV42, 13CrMo4-4, 13CrMo4-5, 15CrMo3, 15CrMo5, 13CrMoV42, 15Cr3, 16MnCr5, 20MnCr5, 15CrMo5, 24CrMo5, 25CrMo4, GS-22CrMo5, GS-22CrMo54, GS 17CrMo5-5, 16CrMoV4, 42CrMo4, 42CrMo4V, 41CrMo4V
 ASTM A 182 Gr. F12; A 193 Gr. B7; A 213 Gr. T12; A 217 Gr. WC6; A 234 Gr. WP11; A335 Gr. P11, P12; A 336 Gr. F11, F12; A 426 Gr. CP12

ZULASSUNGEN CE

SCHWEISSPOSITIONEN

TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	P	S	Cr	Mo
	0.06	0.3	1.2	0.015	0.01	1.1	0.5

MECHANISCHE GÜTEWERTE	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
					RT	-20°C	
	675°C- 705°C 1h	500	630	21	80	55	HRc

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175 M21



CEWELD AA M CrMo1

AA M CRM01 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403032