



CEWELD ULTIMET Alloy Tig

TYPE Cobalt-based solid welding wire for hardfacing / rebuilding

ANWENDUNGEN Wire can be used to weld ULTIMET wrought products and to overlay and clad carbon and low-alloy steels. The weld deposits harden very quickly by cold working. In addition, it is very easy to deposit a "crack-free" layer without a butter layer. The filler metal finish on the MIG wire is for a smooth feeding through welding equipment and reduces tip wear in contact tips.

EIGENSCHAFTEN -ULTIMET wires easily produces crack-free weld deposits (over-matching weld overlays, weld inlays, and claddings). -It is easier to weld with ULTIMET wire than traditional cobalt-based alloys, allowing multiple layer build-ups with no pre-heating needed. -ULTIMET wire produces deposits which harden quickly through peening, machining, power hammering, burnishing, or hard particle impingement. This hardness creates a tough, ductile, wear-, corrosion-, and high-temperature resistant surface. The hardness of 30% cold-worked wrought product is approximately RC50. - ULTIMET deposits exhibit extremely high resistance to metal to metal galling and seizing. -The pitting resistance of ULTIMET alloy in chloride solutions is equal to that of HASTELLOYS C-22HS alloy, and is greater than that of C-276 alloy.

KLASSIFIKATION

GEEIGNET FÜR •Valve component overlay •"Make/break" seal welds in threaded unions •Weld overlays to marine riser tensioners, shafts, and larger hydraulic systems pistons •Weld overlay to u-bends, piping and valves used in conveying sour crudes containing abrasives •Slurry, rock, and acid tumblers & mixers •Impellers •Fiberglass manufacturing

ZULASSUNGEN

SCHWEISSPOSITIONEN



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

| Co | Cr | Ni | Mo | Fe | W | Mn | Si | N | C |
|------|----|----|----|----|---|-----|------|------|------|
| Rem. | 26 | 10 | 5 | 3 | 2 | 0.5 | 0.08 | 0.08 | 0.08 |

MECHANISCHE GÜTEWERTE

| Heat Treatment | R _{P0,2} (MPa) | R _m (MPa) | A ₅ (%) | Hardness |
|----------------|-------------------------|----------------------|--------------------|----------|
| As Welded | | 917 | 13 | HRc |

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175 I1