




# CEWELD OA 62-66B

TYPE	High alloyed seamless metal cored wire for hardfacing against extreme abrasion.												
ANWENDUNGEN	Rebuilding wornout parts or protecting new machine parts to increase life that suffer from extreme abrasive wear												
EIGENSCHAFTEN	High C-, Cr-, B-alloyed flux-cored wire electrode which forms extremely hard carbides for extremely hard deposits on parts subject to excessively heavy abrasive wear weldable with and without protective gas. Extreme good wear resistance due to excellent first layer hardness properties. More than 1 or 2 layers should not be deposited. A Buffer layer with CEWELD® OA 4370 or CEWELD® OA MnCr is recommended in case of old layers or critical base metals..												
KLASSIFIKATION	EN ISO 14700: T Fe15												
GEEIGNET FÜR	62-66 HRc Hardfacing alloy used in mining, agriculture and steel mills, conveyor chains, agriculture, construction, mixer blades, paddles, cement pumps with excellent abrasion and wear resistance against sand and minerals.												
ZULASSUNGEN													
SCHWEISSPOSITIONEN													
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <tr> <td style="width: 16.6%;">C</td> <td style="width: 16.6%;">Si</td> <td style="width: 16.6%;">Mn</td> <td style="width: 16.6%;">Cr</td> <td style="width: 16.6%;">B</td> <td style="width: 16.6%;">Fe</td> </tr> <tr> <td>5</td> <td>1.6</td> <td>1.6</td> <td>27</td> <td>0.45</td> <td>Rem.</td> </tr> </table>	C	Si	Mn	Cr	B	Fe	5	1.6	1.6	27	0.45	Rem.
C	Si	Mn	Cr	B	Fe								
5	1.6	1.6	27	0.45	Rem.								
MECHANISCHE GÜTEWERTE	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <tr> <td style="width: 33%;">Heat Treatment</td> <td style="width: 16.5%;">R<sub>P0,2</sub> (MPa)</td> <td style="width: 16.5%;">R<sub>m</sub> (MPa)</td> <td style="width: 16.5%;">A<sub>5</sub> (%)</td> <td style="width: 16.5%;">Hardness</td> </tr> <tr> <td>As Welded</td> <td></td> <td></td> <td></td> <td>62 HRc</td> </tr> </table>	Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness	As Welded				62 HRc		
Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness									
As Welded				62 HRc									
RÜCKTROCKNUNG	Not required												
HARDNESS HRC	first layer: 58-62HRc, second layer: 62-65HRc												
GAS ACC. EN ISO 14175													



# CEWELD OA 62-66B

OA 62-66B 1,6MM

Packaging	KG/unit	EanCode
BS-300	16	8720663403698