




CEWELD Alu-Flux

TYPE	Flux for aluminium brazing	
ANWENDUNGEN	Alu-Fux is for brazing from Aluminium and Aluminium Alloys with a working range from 350 to 550 °C	
EIGENSCHAFTEN	Usually combined with AlSi12 or AlSi5 filler metal.	
KLASSIFIKATION	EN ISO	18496: FL20
GEEIGNET FÜR	Brazing for Aluminium and Aluminium Alloys with a working range from 350 to 550 °C. Usually combined with AlSi12 or AlSi5 filler metal.	
ZULASSUNGEN		
SCHWEISSPOSITIONEN		
MECHANISCHE GÜTEWERTE		
RÜCKTROCKNUNG	Not required	
GAS ACC. EN ISO 14175		



CEWELD Alu-Flux

ALU-FLUX NAMM

Packaging	KG/unit	EanCode
Jar	0,25	8720663423016