



CEWELD FL 160

TYPE High basic SAW flux with low hydrogen content.

ANWENDUNGEN Boiler works, vessel and structural steel works, tanks and pressure vessels, offshore lifting applications, platforms etc..

EIGENSCHAFTEN FL 160 is a highly basic SAW flux with low hydrogen content. Basicity: about 3 (according to Boniszewski) Current: DC or AC, in single or multi-wires Grain size: 2-20

KLASSIFIKATION EN ISO 14174: SA FB 1 55 AC H5

GEEIGNET FÜR S355, S420, S460, X65, X70, X80

ZULASSUNGEN

SCHWEISSPOSITIONEN



TYPICAL CHEMICAL COMPOSITION IN WEIGHT (%)

Al ₂ O ₃	CaF ₂	SiO ₂	CaO+MgO
20	20	15	40

MECHANISCHE GÜTEWERTE

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175



CEWELD FL 160

FL 160 0,2 - 2,0MM

Packaging	KG/unit	EanCode
Bag	25	8720663404008
Bag	25	8720663404015