



# CEWELD MA 600

**TYPE** 1.4718 Solid 600 HB GMAW welding wire for Mig/Mag hardfacing and rebuilding wornout parts.

**ANWENDUNGEN** Rebuilding and Hardfacing parts that are subject to abrasion combined with heavy impact.

**EIGENSCHAFTEN** CEWELD® MA 600 offers outstanding abrasion resistance combined with heavy shocks, despite the high hardness several layers can be applied without any risk of braking out or chipping of. In case of sensitive base material preheating is recommended at 300-400°C. Old Hardfacing layers should be removed, clean or grind properly before welding.

**KLASSIFIKATION**

AWS	A 5.21: ERFeCr-A
EN ISO	14700: S Fe8
DIN	8555: MSG-6-GZ-60-GP
W.Nr.	1.4718
F-nr	71

**GEEIGNET FÜR** Car recycling, cutters, pumps, stone crushers, knives, scissors, mixers etc.

**ZULASSUNGEN**

**SCHWEISSPOSITIONEN**



**TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)**


C	Mn	Cr	Mo	Nb	V	Fe	W	Si
0.4	0.5	10	0.02	0.005	0.02	Rem.	0.005	3

**MECHANISCHE GÜTEWERTE**

Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness
As Welded				60 HRC

**RÜCKTROCKNUNG** Not required

**GAS ACC. EN ISO 14175** M21



# CEWELD MA 600

MA 600 0,8MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403100

MA 600 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403117
D-200	5	8720663403124

MA 600 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403131
Drum	250	8720682050064

MA 600 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403162