


# CEWELD NiCro 602 CA

TYPE	Nickel based filler metal against extreme temperature conditions.																
ANWENDUNGEN	Welding similar alloys that have to resist extreme high temperature and for cladding steels or stainless steels to obtain a high temperature resistant surface against oxidation.																
EIGENSCHAFTEN	Excellent welding properties with high build-up capacity and low dilution rate. Excellent resistance against temperature cycling conditions up to 1200°C and carburized medias. Excellent fatigue strength and creep properties.																
KLASSIFIKATION	AWS A 5.14: ERNiCrFe-12 EN ISO 18274: S Ni 6025(NiCr25Fe10AlY) W.Nr. 2.4649 F-nr 43 FM 6																
GEEIGNET FÜR	Cladding against high temperature, radiant heater tubes, furnace rolls, muffles in bright annealing furnaces (H <sub>2</sub> atmosphere), rotary kilns, pipe hangers, waste gas components, hydrogen production, methanol and ammonia synthesis, 2.4633, 2.4649, NiCr25FeAlY, Nicrofer 6025 HT, Alloy 602CA, UNS N06025, Centralloy HTE																
ZULASSUNGEN																	
SCHWEISSPOSITIONEN																	
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table><thead><tr><th>C</th><th>Si</th><th>Mn</th><th>Cr</th><th>Ni</th><th>Ti</th><th>Fe</th><th>Al</th></tr></thead><tbody><tr><td>0.2</td><td>0.4</td><td>0.4</td><td>25</td><td>65</td><td>0.15</td><td>10</td><td>2</td></tr></tbody></table>	C	Si	Mn	Cr	Ni	Ti	Fe	Al	0.2	0.4	0.4	25	65	0.15	10	2
C	Si	Mn	Cr	Ni	Ti	Fe	Al										
0.2	0.4	0.4	25	65	0.15	10	2										
MECHANISCHE GÜTEWERTE	<table><thead><tr><th>Heat Treatment</th><th>R<sub>P0,2</sub> (MPa)</th><th>R<sub>m</sub> (MPa)</th><th>A5 (%)</th><th colspan="2">Impact Energy (J) ISO-V</th><th>Hardness</th></tr></thead><tbody><tr><td>As Welded</td><td>520</td><td>750</td><td>26</td><td>RT</td><td>50</td><td>HRc</td></tr></tbody></table>	Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A5 (%)	Impact Energy (J) ISO-V		Hardness	As Welded	520	750	26	RT	50	HRc		
Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A5 (%)	Impact Energy (J) ISO-V		Hardness											
As Welded	520	750	26	RT	50	HRc											
RÜCKTROCKNUNG	Not required																
GAS ACC. EN ISO 14175	I1																



# CEWELD NiCro 602 CA

NICRO 602 CA 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663418333

NICRO 602 CA 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663418340

NICRO 602 CA 1,6MM

Packaging	KG/unit	EanCode
BS-300	10,9	8720663418357