



# CEWELD AlMg 4.5MnZr

<b>TYPE</b>	Mig filler metal for welding Aluminium Magnesium alloys												
<b>ANWENDUNGEN</b>	Construction of ships, off-shore, storage tanks, railways and automotive industry.												
<b>EIGENSCHAFTEN</b>	Special alloy for welding aluminium-magnesium basis alloys with maximum 5% Mg. Zirconium acts as grain-refiner to improve both the bending and the corrosion resistance.Applications in the construction of ships, off-shore, storage tanks, railways and automotive industry.												
<b>KLASSIFIKATION</b>	<table border="0"> <tr> <td>AWS</td> <td>A 5.10: ER5087</td> </tr> <tr> <td>EN ISO</td> <td>18273: S Al 5087 (AlMg4,5MnZr(A))</td> </tr> <tr> <td>W.Nr.</td> <td>3.3546</td> </tr> <tr> <td>F-nr</td> <td>22</td> </tr> </table>	AWS	A 5.10: ER5087	EN ISO	18273: S Al 5087 (AlMg4,5MnZr(A))	W.Nr.	3.3546	F-nr	22				
AWS	A 5.10: ER5087												
EN ISO	18273: S Al 5087 (AlMg4,5MnZr(A))												
W.Nr.	3.3546												
F-nr	22												
<b>GEEIGNET FÜR</b>	<p>Aluminium alloys:</p> <p>AlMg4,5Mn, AlZnMgCu1,5, AlMg5, AlMg3, AlMg5, AlMg2Mn0.8, AlMg2,7Mn, AlZn4,5Mg1, AlZnMg4,5Mn ,AlZn5,5Mg1, AlZn5,5Mg1,5, G-AlMg3Si, G-AlMg5Si, G-AlMg10, G-AlMgSi1, AlMgSiCu 3.3535, 3.3547, 3.3555, ~3.1325, ~3.2315, ~3.4335</p> <p>EN AW 5086, EN AW 6060, EN AW 6005A, EN AW , EN AW 6061, EN AW 7020, EN AW 7021, EN AC 51400, EN AC 51300, EN AC 51100, EN AW 5454</p>												
<b>ZULASSUNGEN</b>	CE												
<b>SCHWEISSPOSITIONEN</b>													
<b>TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)</b>	<table border="1"> <thead> <tr> <th>Mn</th> <th>Cr</th> <th>Ti</th> <th>Al</th> <th>Mg</th> <th>Zr</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>0.1</td> <td>0.15</td> <td>Rem.</td> <td>4.5</td> <td>0.15</td> </tr> </tbody> </table>	Mn	Cr	Ti	Al	Mg	Zr	1	0.1	0.15	Rem.	4.5	0.15
Mn	Cr	Ti	Al	Mg	Zr								
1	0.1	0.15	Rem.	4.5	0.15								
<b>MECHANISCHE GÜTEWERTE</b>	<table border="1"> <thead> <tr> <th>Heat Treatment</th> <th>R<sub>P0.2</sub> (MPa)</th> <th>R<sub>m</sub> (MPa)</th> <th>A<sub>5</sub> (%)</th> <th>Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>140</td> <td>300</td> <td>20</td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R <sub>P0.2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness	As Welded	140	300	20	HRc		
Heat Treatment	R <sub>P0.2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness									
As Welded	140	300	20	HRc									
<b>RÜCKTROCKNUNG</b>	Not required												
<b>GAS ACC. EN ISO 14175</b>	I1, I3												