## CEWELD Powder 8812-Co-45

TYPE	Agglomerated and sintered Tungsten carbide-cobalt powder for Thermal Spraying				
ANWENDUNGEN	CEWELD 8812-Co-45 is an carbide powder for wear resistant coatings produced by flame-, plasma or high-velocityflame-spraying (HVOF). Used to protect against abrasion and friction. Steel Rolls, Conveyor Screws, Impellor Screws, Corrugating Rollers, Exhaust Fans, Pump Housings				
EIGENSCHAFTEN	CEWELD 8812-Co-45 the dense and smooth layers with hardness of up to 1200 HV0.1 and tensile strength acc. to DIN 50160 of more than 70 MPa are frequently used without further treatment. Coating thickness should not exceed 300 $\mu$ m. Maximum operating temperature is 540°C (1004°F). Powder type: agglomerated and sintered Primary WC carbide size: 2.5 $\mu$ m FSSS Apparent density (ISO 3923-2): 4.2-5.5 g/cm <sup>3</sup> Particle shape: preponderantly spherical Particle size: 45/20 $\mu$ m				
KLASSIFIKATION	EN ISO	30 14232-1 WC-Co 88/12			
GEEIGNET FÜR	ldeal for use in a wide variety of high wear applications in-cluding erosion, abrasion and sliding wear. High chrome like finishes can be obtained by typical grinding or lapping techniques.				
ZULASSUNGEN					
SCHWEISSPOSITIONEN	PC				
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	С		Co	WC	
	0.1		12	88	
MECHANISCHE GÜTEWERTE					
RÜCKTROCKNUNG	Not required				

Powder type: agglomerated and sintered Primary WC carbide size: 2.5  $\mu m$  FSSS Apparent density (ISO 3923-2) 4.2-5.5 g/cm³ Particle shape: preponderantly spherical Typical Hardness HV0,3 950 - 1350

GAS ACC. EN ISO 14175

Certilas THE FILLER METAL SPECIALIST