



CEWELD G3

TYPE	Copper-coated filler metal for gas welding. (0,5% Ni, OIII, R60)				
APPLICATIONS	The CEWELD G3 is designed for gas welding unalloyed steels. This process is primarily used for welding plates, pipes, and other profiles where low strength is required.				
PROPERTIES	The CEWELD G3 is designed for gas welding unalloyed steels with a minimum tensile strength of 350 MPa. The resulting joints are homogeneous and soft, and the mechanical properties are excellent.				
CLASSIFICATION	AWS	A 5.2: R60			
	EN ISO	20378: O III			
	F-nr	6			
	FM	1			
SUITABLE FOR	Re ≤ 300 MPa (55 ksi) ISO 15608: 1.1(ReH < 275 MPa) 1.2 (275 < ReH < 300 MPa) 1.0035, 1.0038, 1.0039, 1.0044, 1.0112, 1.0116, 1.0130, 1.0145, 1.0253, 1.0254, 1.0255, 1.0258, 1.0259, 1.0319, 1.0345, 1.0345, 1.0345, 1.0348, 1.0352, 1.0418, 1.0420, 1.0425, 1.0425, 1.0425, 1.0427, 1.0432, 1.0446, 1.0451, 1.0452, 1.0453, 1.0457, 1.0459, 1.0460, 1.0460, 1.0461, 1.0486, 1.0490, 1.0491, 1.0505, 1.0545, 1.0546, 1.0562, 1.0566, 1.0570, 1.0578, 1.0581, 1.0582, 1.1138, 1.5419, 1.8948 C 22.8 S1, S185, S235JRG2, S235JR S235JRH, S275JR, P235S, S235J2G3, P265S, S275J2, P235TR1, P235TR2, P265TR1, P265TR2, P235GH, P235GH, P235GH, P195GH, P245GH, L245ME, GE200, P265GH, P265GH, P265GH, C 22.3, C 21 , GE240, P215NL, P 250, P255QL, P265NL, L245NE, C 22.8, P250GH, P275N, S275N, S275NL, GP240GH, P275SL, 21 Mn 6, StE 320.7, St 52.0, P280GH, (X42ME) L290ME, P305GH, P355GH, P295GH, L290NE, S355N, S355NL, P355N, P355NL1, S355J2G3, G21Mn5, G20Mo5, X52QE, ASTM: A 105, A 27 u. A36 Gr. all; A214; A 242 Gr.1-5; A266 Gr. 1, 2, 4; A283 Gr. A, B, C, D; A285 Gr. A, B, C; A299 Gr. A, B; A328; A366; A515 Gr. 60, 65, 70; A516 Gr. 55; A570 Gr. 30, 33, 36, 40, 45; A 572 Gr. 42, 50; A606 Gr. Alle; A607 Gr. 45; A656 Gr. 50, 60; A668 Gr. A, B; A907 Gr. 30, 33, 36, 40; A841; A851 Gr. 1, 2; A935 Gr.45; A936 Gr. 50; API 5 L Gr. B, X42-X52				
APPROVALS	CE				
WELDING POSITIONS					
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	Ni	
	0.1	0.1	1.1	0.4	
MECHANICAL PROPERTIES	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V
					RT
	As Welded	340	470	20	65
					Hardness
					HRc
REDRYING	Not required				
GAS ACC. EN ISO 14175	None				