



CEWELD OA 64

TYPE Fluxcored wire for hardfacing, weldable without protective gas.

APPLICATIONS Rebuilding wornout parts or protecting new machine parts to increase life that suffer from grinding wear combined with increased temperatures.

PROPERTIES High C-, Cr-, Mo-, Nb-, V-, W-alloyed flux-cored wire electrode which forms extremely hard carbides for extremely hard deposits on parts subject to excessively heavy abrasive wear weldable without protective gas. Extreme good wear resistance even at higher temperatures up to 650°C. More than 1 or 2 layers should not be deposited. Hardness reduction at 400°C app. 4%, at 650°C app. 10%. A Buffer layer with OA 4370 or OA MnCr is recommended in case of old layers or critical base metals. Equivalent in SMAW: Dur 64

CLASSIFICATION EN ISO 14700: T Fe16
DIN 8555: MF 10-GF-65-GZ

SUITABLE FOR For fire gratings, sintering plants, augers and blast furnace bells ,gravel washing equipment, sugar mill hammer and knives, clinker crushers, coal mill rollers, screw conveyors, sintering lines, mixer blades etc.

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)


C	Si	Mn	Cr	Mo	Nb	V	W	B
5	1.4	0.4	21	6	6.2	0.9	2.1	1.8

MECHANICAL PROPERTIES

Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				64 HRc

REDRYING 140°C / 24 hr

GAS ACC. EN ISO 14175



CEWELD OA 64

OA 64 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403742

OA 64 2,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403759

OA 64 2,4MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403766

OA 64 2,8MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403773