



CEWELD AA 316L

TYPE	Flux cored stainless steel welding wire for AISI 316. (Type 19 12 3 L, 1.4430)						
APPLICATIONS	Boilers, shipbuilding, machinery, offshore application, foundries, chemical industry, orbital tube welding etc.						
PROPERTIES	Flux cored wire with slag support for high productivity. Excellent for use on ceramic backing strips. The slag is self detaching and offers extra protection to obtain X-ray proof weld seams with practically no spatters. Better wetting and welding properties with more productivity compared to solid wires. The 0,9 and 1,0 mm can be used for all positions including vertical down and is classified as: AWS A 5.22: E 316-LT1-4						
CLASSIFICATION	AWS	A 5.22: E316LT0-1, A 5.22: E316LT0-4					
	EN ISO	17633-A: T 19 12 3 L R M21 3					
	W.Nr.	1.4430					
	F-nr	6					
	FM	5					
SUITABLE FOR	ISO 15608: 8.1 Austenitic ≤ 19 % Cr , TÜV 1000: Gr. 21-30, 1.4583, 1.4435, 1.4436, 1.4404, 1.4406, 1.4408, 1.4401, 1.4571, 1.4580, 1.4406, 1.4521, 1.4301, 1.4306, X102CrNiMoNb 18 12, X2CrNiMo 18 14 3 (TP), X4CrNiMo 17 13 3, X2CrNiMo 17 12 2 (TP), X 5CrNiMo 19 11 2, X4CrNiMo 17 12 2 (TP), X6CrNiMo 17 12 2, X6CrNiMoNb 17 12 3, X2CrNiMoN 17 12 3 (TP), X2CrMoTi18-2 316Cb, 316L, 316L, 316LN, 316H, 316, 316Ti, 316Cb, 316LN, 444 S31640, S31603, S31653, S31600, S31630, S44400						
APPROVALS	CE						
WELDING POSITIONS	 PA  PB  PC  PF						
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	Cr	Ni	Mo	Cu
	0.028	0.51	1.63	18.9	12.1	2.75	0.11
MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
					RT	-110°C	
	As Welded	380	525	45	55	35	HRc
REDRYING	140°C / 24 hr						
GAS ACC. EN ISO 14175	M21						



CEWELD AA 316L

AA 316L 0,9MM

Packaging	KG/unit	EanCode
BS-300	12,5	8720663413352
D-200	4,5	8720663413437

AA 316L 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663413505
BS-300	12.5	8720663413512
D-200	5	8720663413567

AA 316L 1,6MM

Packaging	KG/unit	EanCode
BS-300	17	8720663413536