



CEWELD E NiCro HLS

TYPE Basic coated electrode for joining and cladding. Excellent for similiary and dissimilar materials and for difficult to weld steels. (Type E 6082, E NiCrFe3)

APPLICATIONS **CEWELD® E NiCro HLS** is the electrode of choice for joint welding of steel with nickel alloys or repair of high carbon steels and white cast iron. **CEWELD® E NiCro HLS** is suitable for maintenance and new welds in the chemical, apparatus and heavy industry, furnace repair, unknown steel, cock wheels, chains. As well as for welding mixed joints with Inconel, Hasteloy, Nimonic, stainless steel and difficult-to-weld steel

PROPERTIES **CEWELD® E NiCro HLS** has an extremely crack-resistant weld metal due to the special basic coating and its alloy properties. Suitable for working temperatures between -196 °C and +650 °C. The yield is 150% with excellent arc stability and easy slag removal.

CLASSIFICATION

AWS	A 5.11: E NiCrFe-3
EN ISO	14172: E Ni 6082
W.Nr.	2.4648
F-nr	~43
FM	6

SUITABLE FOR **Ni 6082 (NiCr20Mn3Nb), ENiCrFe-3**
 1.4429, 1.4539, 1.4583, 1.4816, 1.4876, 1.5662, 1.5680, 1.5637, 1.6582, 2.4669, 2.4806, 2.4816, 2.4851, 2.4867, 2.4951,
 X10NiCrAlTi3 2 20, X10CrNiMoNb18 12,NiCr20Ti, X 2 CrNiMoN 17-12-3, X 1 NiCrMoCu 25-20-5,X 8 NiCrAlTi 32-21,
 X 20 CrMoV 11-1, X 8 Ni 9, NiCr 15 Fe, NiCr 6015, NiCr 10
AISI 4340, 4130, 8630
ASTM B163, B166, B167 und B168
UNS: K 81340, N06600, N 06601, N 08800, N 08810.
 Incoloy 800, DS - Inconel 600, 601, Alloy 82, Alloy 80A, Alloy X750,

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

C	Si	Mn	Cr	Ni	Fe	Nb
0.06	0.5	5	20	70	3	2.5

MECHANICAL PROPERTIES

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
				RT	-196°C	
As Welded	400	650	35	90	70	HRc

REDRYING 300°C / 2 hr

GAS ACC. EN ISO 14175



CEWELD E NiCro HLS

E NICRO HLS 2,5 X 350MM	Packaging	KG/unit	EanCode
	Can	3	8720663418586
E NICRO HLS 3,2 X 350MM	Packaging	KG/unit	EanCode
	Can	2,8	8720663418593
E NICRO HLS 4,0 X 350MM	Packaging	KG/unit	EanCode
	Can	2,5	8720663418609
E NICRO HLS 5,0 X 350MM	Packaging	KG/unit	EanCode
	Can	3.5	8720663418616