



# CEWELD S4 MoSi

**TYPE** Solid wire for submerged arc welding with high Manganese content and 0,5% Mo.

**APPLICATIONS** Fine grain steels for yield strength applications exceeding 500 MPa. Often used for pipe welding (X70-X80) when Mn. and Si. content is low..

**PROPERTIES** High Manganese and Silicon content for improved de-oxidation and strength, excellent wetting for increased welding speed with corresponding flux. Suitable fluxes are depending on the weld metal requirements, in most cases CEWELD® FL 155 gives excellent results.


**CLASSIFICATION**

AWS	A 5.23: EA3K
EN ISO	14341-A: G4Mo
F-nr	6
FM	3

**SUITABLE FOR** Pipe steels acc. to ISO 3183, EN 10208 and API-5: L360N/X52 to L555Q/X80

**APPROVALS**

**WELDING POSITIONS**



**TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)**

C	Si	Mn	P	S	Mo
0.1	0.7	1.8	0.015	0.015	0.5

**MECHANICAL PROPERTIES**

Heat Treatment	R <sub>PO,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V				Hardness
				-20°C	-40°C	0°C	-30°C	
As Welded				60	50	HRc		
580°C±15°C 2h	550	680	20	80	60	50	HRc	

**REDRYING** Not required

**GAS ACC. EN ISO 14175**



# CEWELD S4 MoSi

S4 MOSI 4,0MM

Packaging	KG/unit	EanCode
K-415	25	8720663404701