


CEWELD MA SS 2343

TYPE	Solid welding wire for hardfacing and rebuilding hotworking tools..					
APPLICATIONS	Rebuilding and hardfacing parts that are subject to abrasion combined with higher temperatures.					
PROPRIÉTÉS	Abrasion combined with higher temperatures.					
CLASSIFICATION	EN ISO W.Nr.	14700: S Fe3 1.2343				
CONVIENT POUR	Hotworking tools, high speed tool steels, HSS, aluminium press molts, dies, stamping tools, cutting tools, shear blades, cutters, knives, scissors.					
AGRÉMENTS						
POSITIONS DE SOUDAGE	      					
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)	C 0.4	Mn 0.4	Cr 5	Mo 1.1	V 0.5	Fe Rem. Si 1
PROPRIÉTÉS MÉCANIQUES	Heat Treatment As Welded		R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness 55 HRc
ETUVAGE	Not required					
GAS ACC. EN ISO 14175	M21					



CEWELD MA SS 2343

MA SS 2343 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663401786

MA SS 2343 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663401779