

CEWELD OA 550-VW

TYPE Medium -alloyed tubular wire on a C-Cr-Mo-W basis for high hardness up to 550°C.

APPLICATIONS Recommended for parts subject to strong mineral abrasion and erosion, .

PROPRIÉTÉS Very good abrasion resistance in combination with impact even at higher temperatures up to 550°C. To much layers should be avoided, preheat is necessary to avoid cracking. A buffer layer with OA 4370 or OA MnCr is recommended in case of sensible basematerial or old layers. Weldable without protective gas.

CLASSIFICATION EN ISO 14700: T Fe6
DIN 8555: MF 6-60-PT

CONVIENT POUR HRc 55-58, Cement pumps, crusher bars, hammer and blooming table rolls, mineral and brick industry.

AGRÉMENTS

POSITIONS DE SOUDAGE



**ANALYSE CHIMIQUE
TYPIQUE DU MÉTAL DE
SOUDURE (%)**


C	Si	Mn	Cr	Mo	V	Fe	W
0.55	0.9	2.8	7	1.6	1.8	Rem.	0.9

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				55 HRc

ETUVAGE 140°C / 24 hr

GAS ACC. EN ISO 14175



CEWELD OA 550-VW

OA 550-VW 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403315

OA 550-VW 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403490

OA 550-VW 2,8MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403414