




# CEWELD AA 2209P

TYPE	Rutile fluxcored wire for welding duplex stainless steels																													
APPLICATIONS	Duplex stainless steels in chemical industry such as offshore, tubing, vessel, boilers etc..																													
PROPRIÉTÉS	Smooth drop transfer and stable arc with no spatter losses. High productivity and weldability, better wetting properties compared to solid wires. Ductile weld metal quality and X-ray soundness with easy slag removal and ferrite level between 30 and 50 (FN). Excellent for use in position and down hand welding. Excellent against pitting and stress corrosion. The PREN above 35 weldmetal offers outstanding resistance against pitting.																													
CLASSIFICATION	AWS	A 5.22: E2209T1-4																												
	EN ISO	17633-A: T 22 9 3 N L P M21 2																												
	W.Nr.	1.4462																												
	F-nr	6																												
	FM	5																												
CONVIENT POUR	<b>ISO 15608: 10.1-10.2 Austenitic &gt; 24 % Cr ≤ 4% Ni, DUPLEX 2209, 22%Cr 9%Ni 3%Mo</b> 1.4417, 1.4462, 1.4362, 1.4162, 1.4463, 1.4460, 1.4583 X 2 CrNiMoSi 19 5, X 2 CrNiN 23 4, X 2 CrNiMoN 22 5 3, X10CrNiMoNb18-12 316LN, 318LN UNS S31803, S32205, S32304 SAF 2205 Fafer 4462, NKCr22, SM22Cr, Falc 223 UR 45N & UR 45N+, 2101, 2205, UR 35 N SAF 2304 mix 1.4462 X2CrNiMoN22-5-3 mit P235GH/ P265GH, S255N, P295GH, S355N, 16Mo3																													
AGRÉMENTS	CE, Lloyds: LR23315606WC, DNV: TAW00005FD																													
POSITIONS DE SOUDAGE																														
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>N</th> <th>FNW</th> </tr> </thead> <tbody> <tr> <td>0.03</td> <td>0.5</td> <td>1.1</td> <td>0.01</td> <td>0.009</td> <td>23.1</td> <td>8.9</td> <td>3.6</td> <td>0.11</td> <td>49</td> </tr> </tbody> </table>										C	Si	Mn	P	S	Cr	Ni	Mo	N	FNW	0.03	0.5	1.1	0.01	0.009	23.1	8.9	3.6	0.11	49
C	Si	Mn	P	S	Cr	Ni	Mo	N	FNW																					
0.03	0.5	1.1	0.01	0.009	23.1	8.9	3.6	0.11	49																					
PROPRIÉTÉS MÉCANIQUES	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R<sub>p0,2</sub> (MPa)</th> <th rowspan="2">R<sub>m</sub> (MPa)</th> <th rowspan="2">A<sub>5</sub> (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th>-40°C</th> <th>-60°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>650</td> <td>825</td> <td>28</td> <td>42</td> <td>35</td> <td>HRc</td> </tr> </tbody> </table>							Heat Treatment	R <sub>p0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V		Hardness	-40°C	-60°C	As Welded	650	825	28	42	35	HRc							
Heat Treatment	R <sub>p0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V		Hardness																								
				-40°C	-60°C																									
As Welded	650	825	28	42	35	HRc																								
ETUVAGE	140°C / 24 hr																													
GAS ACC. EN ISO 14175	M21																													



# CEWELD AA 2209P

AA 2209P 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663414748
D-200	5	8720663414762
D-270	15	8720663424648