



CEWELD FL 160

TYPE High basic SAW flux with low hydrogen content.

APPLICATIONS Boiler works, vessel and structural steel works, tanks and pressure vessels, offshore lifting applications, platforms etc..

PROPRIÉTÉS FL 160 is a highly basic SAW flux with low hydrogen content. Basicity: about 3 (according to Boniszewski) Current: DC or AC, in single or multi-wires Grain size: 2-20

CLASSIFICATION EN ISO 14174: SA FB 1 55 AC H5

CONVIENT POUR S355, S420, S460, X65, X70, X80

AGRÉMENTS

POSITIONS DE SOUDAGE



TYPICAL CHEMICAL COMPOSITION IN WEIGHT (%)

Al2O3	CaF2	SiO2	CaO+MgO
20	20	15	40

PROPRIÉTÉS MÉCANIQUES

ETUVAGE Not required

GAS ACC. EN ISO 14175



CEWELD FL 160

FL 160 0,2 - 2,0MM

Packaging	KG/unit	EanCode
Bag	25	8720663404008
Bag	25	8720663404015