



CEWELD AA R500SR

TYPE	Seamless copper coated rutile flux-cored wire for M21.																							
APPLICATIONS	Offshore, Shipbuilding, pressure vessels, orbital pipe work.																							
PROPRIÉTÉS	AA R500 SR is a seamless rutile cored wire and has excellent modelling ability, therefore excellent forced position welding in all positions at high amperage. Down to -60 °C very good impact values are achieved also with very good PWHT results. Particularly suitable for welding on ceramics in all positions. Low spatter losses, easily removable slag.																							
CLASSIFICATION	AWS	A 5.29: E81T1-Ni1M-J H4, A 5.36: E81T1-M21A8-Ni1-H4																						
	EN ISO	17632-A: T 50 6 1Ni P M21 1 H5																						
CONVIENT POUR	ReH ≤ 500 MPa ISO 15608: 1.1, 1.3, 2.1, 2.2 (ReH max. 500 MPa), 3.1 (ReH max. 500 MPa) 1.0580 to 1.0070, 1.8900 to 1.8905, 1.8930 to 1.8935, 1.8910 to 1.8915, 1.6217, 1.6210, 1.0481, 1.0482, 1.0551, 1.0553. S275N-S460N, S275NL-S460NL, S275M-S460M, S275ML-S460ML, P355N, P355NH, P460N, P460NH, P275NL1-P460NL1, P275NL2- P460NL2, L360NB, L415NB, L360MB-L450MB, L360QB-L450QB ASTM A 203 Gr. D, E; A 350 Gr. LF1, LF2, LF3; A 420 Gr. WPL3, WPL6; A 516 Gr. 60, 65, 70; A 572 Gr. 42, 50, 55, 60, 65; A 633 Gr. A, D, E; A 662 Gr. A, B, C; A 707 Gr. L1, L2, L3; A 738 Gr. A; A 841 A, B, C; API 5 L X52, X60, X65, X52Q, X60Q, X65Q, X70Q Oceanfit 52, Oceanfit 60, Oceanfit 65, Oceanfit 355, Oceanfit 420, Oceanfit 460, alform plate 460M; durostat 400, 450, 500, durostat B2, aldur 500Q, aldur 500QL, aldur 500QL1, N-A-XTRA 56																							
AGRÉMENTS	CE																							
POSITIONS DE SOUDAGE																								
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL DE SOUDURE (%)	<table><tr><td>C</td><td>Si</td><td>Mn</td><td>P</td><td>S</td><td>Ni</td></tr><tr><td>0.08</td><td>0.5</td><td>1.4</td><td>0.015</td><td>0.015</td><td>0.9</td></tr></table>					C	Si	Mn	P	S	Ni	0.08	0.5	1.4	0.015	0.015	0.9							
C	Si	Mn	P	S	Ni																			
0.08	0.5	1.4	0.015	0.015	0.9																			
PROPRIÉTÉS MÉCANIQUES	<table><tr><th rowspan="2">Heat Treatment</th><th rowspan="2">R_{P0,2} (MPa)</th><th rowspan="2">R_m (MPa)</th><th rowspan="2">A₅ (%)</th><th>Impact Energy (J) ISO-V</th><th rowspan="2">Hardness</th></tr><tr><th>-60°C</th></tr><tr><td>As Welded</td><td>550</td><td>600</td><td>22</td><td>70</td><td>HRc</td></tr><tr><td>570°C- 620°C 1h</td><td>520</td><td>580</td><td>22</td><td>50</td><td>HRc</td></tr></table>					Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	Hardness	-60°C	As Welded	550	600	22	70	HRc	570°C- 620°C 1h	520	580	22	50	HRc
Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	Hardness																			
				-60°C																				
As Welded	550	600	22	70	HRc																			
570°C- 620°C 1h	520	580	22	50	HRc																			
ETUVAGE	Not required																							
GAS ACC. EN ISO 14175	M21																							



CEWELD AA R500SR

AA R500SR 1,2MM

Packaging	KG/unit	EanCode
BS-300	16	8720663424563