



CEWELD AA 318

| TYPE | Gestabiliseerde roestvrijstalen rutiel gevulde draad met hoog Mo-gehalte | | | | | | | | | | | | | | | | | | |
|--|--|----------------|-------------------------|----------------------|--------------------|-------------------------|--------------------|----------|-------------------------|----|-----------|------|------|-------|------|------|------|-------|------|
| TOEPASSINGEN | Ontwikkeld voor het lassen van gestabiliseerde CrNi(N) en CrNiMo(N) types. | | | | | | | | | | | | | | | | | | |
| EIGENSCHAPPEN | Gevulde draad met slakondersteuning voor lassen met hoge productiviteit in alle posities. Uitstekend geschikt voor gebruik op keramische backingstrips. De slak laat zichzelf los en biedt extra bescherming om hoogwaardige lasnaden te verkrijgen met praktisch geen spatten. Betere bevochtigings- en laseigenschappen met meer productiviteit in vergelijking met massieve draden. | | | | | | | | | | | | | | | | | | |
| CLASSIFICATIE | EN ISO 17633-A: T 19 12 3 Nb P M21 1 W.Nr. 1.4576 FM 5 | | | | | | | | | | | | | | | | | | |
| GESCHIKT VOOR | 1.4301, 1.4306, 1.4401, 1.4404, 1.4408, 1.4420, 1.4435, 1.4436, 1.4541, 1.4550, 1.4571, 1.4573, 1.4580, 1.4581, 1.4583 X 6 CrNiMoTi 17 12 2, X10 CrNiMoTi 18 12, X 6 CrNiMoNb 17 12 2, G-X 5 CrNiMoNb 18 10, X 10 CrNiMoNb 18 12, X 5 CrNiMo 18 11, X 2 CrNiMo 17 13 2, G-X 2 CrNiMo 18 10, X 2 CrNiMo 18 14 3, X 5 CrNiMo 17 12 2, G-X 6 CrNiMo 18 10, X 5 CrNiMo 17 13 3 UNS S31600, S31603, S31635, S31640, S31653, AISI 316, 316L, 316Ti, 316Cb | | | | | | | | | | | | | | | | | | |
| GOEDKEURINGEN | CE | | | | | | | | | | | | | | | | | | |
| LASPOSITIES | | | | | | | | | | | | | | | | | | | |
| TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%) | <table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Cu</th> <th>N</th> <th>Nb</th> </tr> </thead> <tbody> <tr> <td>0.029</td> <td>0.58</td> <td>1.34</td> <td>18.64</td> <td>11.5</td> <td>2.78</td> <td>0.05</td> <td>0.032</td> <td>0.36</td> </tr> </tbody> </table> | C | Si | Mn | Cr | Ni | Mo | Cu | N | Nb | 0.029 | 0.58 | 1.34 | 18.64 | 11.5 | 2.78 | 0.05 | 0.032 | 0.36 |
| C | Si | Mn | Cr | Ni | Mo | Cu | N | Nb | | | | | | | | | | | |
| 0.029 | 0.58 | 1.34 | 18.64 | 11.5 | 2.78 | 0.05 | 0.032 | 0.36 | | | | | | | | | | | |
| MECHANISCHE WAARDEN | <table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0.2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">0°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>500</td> <td>670</td> <td>31</td> <td colspan="2">60</td> <td>HRC</td> </tr> </tbody> </table> | Heat Treatment | R _{P0.2} (MPa) | R _m (MPa) | A ₅ (%) | Impact Energy (J) ISO-V | | Hardness | 0°C | | As Welded | 500 | 670 | 31 | 60 | | HRC | | |
| Heat Treatment | R _{P0.2} (MPa) | | | | | R _m (MPa) | A ₅ (%) | | Impact Energy (J) ISO-V | | Hardness | | | | | | | | |
| | | 0°C | | | | | | | | | | | | | | | | | |
| As Welded | 500 | 670 | 31 | 60 | | HRC | | | | | | | | | | | | | |
| HERDROGEN | 140°C / 24 hr | | | | | | | | | | | | | | | | | | |
| GAS ACC. EN ISO 14175 | M21 | | | | | | | | | | | | | | | | | | |



CEWELD AA 318

AA 318 1,2MM

| Packaging | KG/unit | EanCode |
|-----------|---------|---------------|
| BS-300 | 15 | 8720663413635 |