

CEWELD E DUR 71

TYPE	Basic coated electrode with a sintered tungsten carbide core wire.
TOEPASSINGEN	For extreme wear resistance, elements as Niobium and Chromium carbides are also added to obtain a complex carbide structure. Specially used for applications subject to abrasive wear such as sand or other minerals with little impact. Recommended for the brick and clay industry or extreme high temperature applications in power plant industries.
EIGENSCHAPPEN	CEWELD E DUR 71 is designed to offer full wear resistance and high hardness already achieved in the first layer. To be welded with low as possible current to avoid burnout of elements.
CLASSIFICATIE	
GESCHIKT VOOR	For extreme heavy abrasion and wear applications such as, mixers and screws in the brick and clay industry, electricity powerplant screws (ash), mining, drilling etc
GOEDKEURINGEN	
LASPOSITIES	



MECHANISCHE WAARDEN	Heat Treatment	$R_{P0,2}$ (MPa)	R_m (MPa)	A5 (%)	Hardness
	As Welded				65 HRc

HERDROGEN	Not required
HARDNESS HRC	first layer: $\pm 63-65$ HRc second layer: $\pm 66-70$ HRc
GAS ACC. EN ISO 14175	

CEWELD E DUR 71

E DUR 71 3,2 X 350MM

Packaging	KG/unit	EanCode
Can	2,5	8720663402721

E DUR 71 4,0 X 350MM

Packaging	KG/unit	EanCode
Can	2,5	8720663402738