



# CEWELD NiCrBSi 4 Tig (Colmony 4)

TYPE	Nickel based Tig filler metal for hardfacing and overlay applications.												
TOEPASSINGEN	NiCrBSi 4 TIG offers outstanding metallurgical and physical properties making them ideally suited to solving wear mechanisms such as abrasion, erosion, corrosion and high-temperatures encountered in service.												
EIGENSCHAPPEN	This nickel based alloy offers superior wear protection, retaining its hardness up to 600°C (1000°F) with significant resistance to oxidation.												
CLASSIFICATIE	AWS                      A 5.21: ERNiCr-A												
GESCHIKT VOOR	<b>UNS N99644, DELORO 40 Alloy, Colmony 4</b> Aircraft gas turbines, steam turbine powerplants, turbochargers and valves in reciprocating engines, prosthetic devices, heat treating equipment, pollution control equipment, coal gasification and liquefaction systems, and components in pulp and paper mills.												
GOEDKEURINGEN													
LASPOSITIES													
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th style="width: 16.6%;">C</th> <th style="width: 16.6%;">Ni</th> <th style="width: 16.6%;">Cr</th> <th style="width: 16.6%;">B</th> <th style="width: 16.6%;">Si</th> <th style="width: 16.6%;">Fe</th> </tr> </thead> <tbody> <tr> <td>0.4</td> <td>Rem.</td> <td>10</td> <td>2.4</td> <td>2.1</td> <td>2.8</td> </tr> </tbody> </table>	C	Ni	Cr	B	Si	Fe	0.4	Rem.	10	2.4	2.1	2.8
C	Ni	Cr	B	Si	Fe								
0.4	Rem.	10	2.4	2.1	2.8								
MECHANISCHE WAARDEN	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th style="width: 33.3%;">Heat Treatment</th> <th style="width: 16.6%;">R<sub>P0,2</sub> (MPa)</th> <th style="width: 16.6%;">R<sub>m</sub> (MPa)</th> <th style="width: 16.6%;">A<sub>5</sub> (%)</th> <th style="width: 16.6%;">Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td></td> <td></td> <td></td> <td>40 HRc</td> </tr> </tbody> </table>	Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness	As Welded				40 HRc		
Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness									
As Welded				40 HRc									
HERDROGEN	Not required												
GAS ACC. EN ISO 14175	11												