



CEWELD AA R610

TYPE	Seamless micro alloyed rutile cored wire with slag for M21																		
TOEPASSINGEN	Offshore, Shipbuilding, pressure vessels, orbital pipe work respecting the NACE requirements. Steels with yield strength up to 620 MPa (90 ksi).																		
EIGENSCHAPPEN	Very good modeling ability, therefore excellent all-position welding with higher currents. For use down to -40 °C (- 40 °F) .. Particularly suitable for MAG-orbital welding and for weldings on ceramics in all positions. Low spatter loss, and remarkable easy slag removal.																		
CLASSIFICATIE	<table border="0"> <tr> <td>AWS</td> <td>A 5.29: E101T1-K2M H4</td> </tr> <tr> <td>EN ISO</td> <td>18276-A: T 62 4 Mn1Ni P M21 1 H5</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>2</td> </tr> </table>	AWS	A 5.29: E101T1-K2M H4	EN ISO	18276-A: T 62 4 Mn1Ni P M21 1 H5	F-nr	6	FM	2										
AWS	A 5.29: E101T1-K2M H4																		
EN ISO	18276-A: T 62 4 Mn1Ni P M21 1 H5																		
F-nr	6																		
FM	2																		
GESCHIKT VOOR	<p>Reh ≤ 620 MPa ISO 15608: ~3.1, 2.2</p> <p>1.8864, 1.8873, 1.8881, 1.8928, 1.8977, 1.8924, 1.8909, 1.8984, 1.8926, 1.8904, 1.8986 S500Q-S620Q, S500QL-S620QL, L485MB-L555MB, L485QB-L555QB, 620 M, PAS 460-550 ASTM A 572 Gr. 65; A 633 Gr. E; A 738 Gr. A; A 852; API 5 L X70, X80, X70Q, X80Q alform 500 M, 550 M, 600 M, aldur 550 Q, Dillimax 550, Dillimax 500, Domex 500, Domex 550</p>																		
GOEDKEURINGEN	CE																		
LASPOSITIES																			
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>0.062</td> <td>0.55</td> <td>1.6</td> <td>0.006</td> <td>0.014</td> <td>0.02</td> <td>0.98</td> <td>0.012</td> <td>0.07</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Cr	Ni	Mo	Cu	0.062	0.55	1.6	0.006	0.014	0.02	0.98	0.012	0.07
C	Si	Mn	P	S	Cr	Ni	Mo	Cu											
0.062	0.55	1.6	0.006	0.014	0.02	0.98	0.012	0.07											
MECHANISCHE WAARDEN	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0,2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">-40°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>635</td> <td>715</td> <td>28</td> <td colspan="2">105</td> <td>HRC</td> </tr> </tbody> </table>	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	-40°C		As Welded	635	715	28	105		HRC		
Heat Treatment	R _{P0,2} (MPa)					R _m (MPa)	A ₅ (%)		Impact Energy (J) ISO-V		Hardness								
		-40°C																	
As Welded	635	715	28	105		HRC													
HERDROGEN	Not required																		
GAS ACC. EN ISO 14175	M21																		



CEWELD AA R610

AA R610 1,2MM

Packaging	KG/unit	EanCode
D-200	20 (4x5)	8720663423702
K-300	16	8720663423719