


# CEWELD CuNi10Zn42

TYPE	CuZnNi alloyed brazing alloy with excellent strength			
TOEPASSINGEN	Joining: Steels, Galvanized steel, Tempered Cast Iron, Cast iron, Nickel alloys etc. This alloy is mainly used in the furniture and the bicycle industry for high strength joining of steels, also is this alloy recommended for rebuilding cock wheels due to the good sliding properties.			
EIGENSCHAPPEN	Good flowing high strength Ni-brass alloy containing Nickel for more strength and bridging capability during brazing with excellent rebuilding properties. Flux/Paste: CEWELD Universal-Flux			
CLASSIFICATIE	AWS	A 5.8: RBCuZn-D		
	EN ISO	17672: Cu 773		
	W.Nr.	2.0711		
	F-nr	35		
GESCHIKT VOOR	Steels, Galvanized steel, Tempered Cast Iron, Cast iron, Nickel alloys			
GOEDKEURINGEN				
LASPOSITIES				
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Si	Ni	Cu	Zn
	0.1	10	48	Rem.
MECHANISCHE WAARDEN	Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A5 (%)
	As Welded		785	
HERDROGEN	Not required			
MELTING RANGE	890 - 920°C			
GAS ACC. EN ISO 14175				