



CEWELD FL 860 ESHC

TYPE High basic agglomerated flux for welding Nickel based strips with the elctro slag process.

TOEPASSINGEN Designed for ES strip cladding in offshore, apparatus, vessel, boilers and chemical industry.

EIGENSCHAPPEN FL 860 ESHC is a highly basic flux for Nickel based strip electro slag cladding. Basicity: about 4,2 (according to Boniszewski) Current: DC + Grain size: 2-16

CLASSIFICATIE EN ISO 14174: ES A FB 2B 5644 DC

GESCHIKT VOOR Electro slag cladding with nickel based strip, Inconel 600, 625, 825, alloy 82 and 625, W.Nr: 2.4806, 2.4831, 2.4633, 2.4649, Nicrofer 6025HT, Alloy 602 CA.

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL COMPOSITION IN WEIGHT (%)

CaF2	SiO2	CaO+MgO
70	20	5

MECHANISCHE WAARDEN

HERDROGEN Not required

GAS ACC. EN ISO 14175



CEWELD FL 860 ESHC

FL 860 ESHC 0,2 - 1,6MM

Packaging	KG/unit	EanCode
Bag	25	8720663404213