

TYPE	Tin bronze alloy with high percentage of tin for virtually all welding procedures					
TOEPASSINGEN	Boilers and tubes out of copper or copper alloys, oven soldering etc.					
EIGENSCHAPPEN	Very good deoxidization and high hardness similar to cast bronzes. Surfacing and joining of Copper and CuSn-Alloys. Widely used and recommended for oven soldering. High quality alloyed copper wire. Sound, pore free deposits and good electrical conductivity. Excellent corrosion resistance					
CLASSIFICATIE	EN ISO W.Nr.	24373: Cu 5410 / CuSn12P 2.1056				
GESCHIKT VOOR	Tin bronze alloy with high percentage of tin for virtually all welding procedures. Very good deoxidisation and high hardness similar to cast bronzes. Surfacing and joining of Copper and CuSn- alloys. Widely used and recommended for oven soldering. Mat.n: 2.1016, 2.1020, 2.1030, 2.1050, 2.1052, 2.1056, 2.1080, 2.1086, 2.1090 CuSn8, CuSn7, CuSn6, CuSn4, G-CuSn7ZnPb, G-CuSn10					
GOEDKEURINGEN						
LASPOSITIES	PA PB PC PD PE PF PG					
TYPICAL CHEMICAL	Р	Cu	Zn	Pb	Sn	
ANALYSIS OF THE FILLER METAL (%)	0.25	Rem.	0.03	0.01	12	
		I	1			

MECHANISCHE WAARDEN	Heat Treatment	R _{P0,2} (MPa)	Rm (MPa)	A5 (%)	Hardness
	As Welded		350		120 HB

HERDROGEN	Not

required

GAS ACC. EN ISO 14175 I1





CEWELD CuSn12 Tig

CUSN12 TIG 1,6 X 1000MM	Packaging	KG/unit	EanCode	
	Tube	5	8720663422835	
CUSN12 TIG 2,0 X 1000MM	Packaging	KG/unit	EanCode	
	Tube	5	8720663422842	
CUSN12 TIG 3,0 X 1000MM	Packaging	KG/unit	EanCode	
	Tube	5	8720663422859	
CUSN12 TIG 4,0 X 1000MM	Packaging	KG/unit	EanCode	
	Tube	5	8720663422866	