



# CEWELD MA 350

<b>TYPE</b>	Welding wire for rebuilding parts and for buffer layers before hardfacing.	
<b>TOEPASSINGEN</b>	Rebuilding machine parts before Hardfacing and cladding crane and or train wheels to achieve a wear resistant layer against high pressure caused by metal to metal friction.	
<b>EIGENSCHAPPEN</b>	CEWELD MA 350 offers almost full hardness in the first layer and can be applied without any risk of cracking. Multiple layers or sandwich layers are possible before Hardfacing and will help to increase the hardness (wear resistance) from the hardface layer.	
<b>CLASSIFICATIE</b>	AWS	A 5.21: ERFe-1
	EN ISO	14700: S Fe2
	DIN	8555: MSG-5-GZ-350
	W.Nr.	~1.7363
	F-nr	71

**GESCHIKT VOOR** 350 HB hardfaing alloy, sprocket wheels, rebuilding, crushing hammers, Rebuilding machine parts before hardfacing and cladding crane and or train wheels to achieve a wear resistant layer against high pressure caused by metal to metal friction.

**GOEDKEURINGEN**

**LASPOSITIES**



**TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)**

C	Mn	Cr	Ni	Mo	Fe
0.08	0.5	6	0.1	0.5	Rem.

**MECHANISCHE WAARDEN**

Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness
As Welded				360 HB

**HERDROGEN** Not required

**GAS ACC. EN ISO 14175** M21



# CEWELD MA 350

MA 350 0,8MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403056

MA 350 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403063

MA 350 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403070

MA 350 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403094