



CEWELD DUR 6 Tig

TYPE	Cobalt-based thermo shock resistant alloy for overlay applications.															
TOEPASSINGEN	Steam-valves, high temperature liquid pumps, hot cutting tools, exhaust valves.															
EIGENSCHAPPEN	Outstanding alloy against abrasion, thermo-shock and corrosion combined with high temperatures. The weld deposit can be machined with tungsten tool tips and by grinding. The hardness of the weld deposit will decrease 16% at 300°C and about 30% at 600°C. The weld deposit is high heat resistant up to 900°C. DUR 6 offers a low coefficient of friction of 0.12 and exceptional resistance to galling. It has cavitation-erosion resistance ten times that of 304 stainless steel, DUR 6 can be used to protect bearing surfaces in non-lubricating conditions due to its resistance to metal-to-metal wear.															
CLASSIFICATIE	AWS EN ISO F-nr	A 5.21: ERCoCr-A 14700: S Co2 71														
GESCHIKT VOOR	Stellite 6 alloy for, Steam-valves, high temperature liquid pumps, hot cutting tools, exhaust valves and seats															
GOEDKEURINGEN																
LASPOSITIES																
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1" style="width: 100%; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Fe</th> <th>W</th> <th>Co</th> </tr> </thead> <tbody> <tr> <td>1.1</td> <td>1</td> <td>0.6</td> <td>28</td> <td>2.5</td> <td>5</td> <td>Rem.</td> </tr> </tbody> </table>		C	Si	Mn	Cr	Fe	W	Co	1.1	1	0.6	28	2.5	5	Rem.
C	Si	Mn	Cr	Fe	W	Co										
1.1	1	0.6	28	2.5	5	Rem.										
MECHANISCHE WAARDEN	<table border="1" style="width: 100%; text-align: center;"> <thead> <tr> <th>Heat Treatment</th> <th>R_{P0,2} (MPa)</th> <th>R_m (MPa)</th> <th>A₅ (%)</th> <th>Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td></td> <td></td> <td></td> <td>40 HRc</td> </tr> </tbody> </table>		Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness	As Welded				40 HRc				
Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness												
As Welded				40 HRc												
HERDROGEN	Not required															
GAS ACC. EN ISO 14175	I1															



CEWELD DUR 6 Tig

DUR 6 TIG 2,4 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663402271
DUR 6 TIG 3,2 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663402288
DUR 6 TIG 4,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663402295
DUR 6 TIG 5,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663402301
DUR 6 TIG 6,4 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663402318