



CEWELD NiCro 625 Tig

| TYPE | Solid nickel base welding rod for tungsten inert gas welding | | | | | | | | | | | | | | | | |
|---|--|----------------|-------------------------|----------------------|--------------------------------|-------------------------|--------------------|----------|-------------------------|--------|-----------|-----|-----|----|-----|-----|-----|
| TOEPASSINGEN | CEWELD® NiCro 625 Tig is developed for welding and cladding nickel-based alloys such as alloy 625 or similar materials. This alloy can also be used for welding dissimilar nickel-based alloys to each other, to alloyed steels or to stainless steels and for joining 6% molybdenum super austenitic steels. Nicro 625 is most commonly used in the chemical processing industry, pollution control equipment, marine equipment, nuclear reactor components, pump shafts. Also used in the aerospace industry for thrust reverser assemblies, fuel nozzles, after-burners and combustion systems. | | | | | | | | | | | | | | | | |
| EIGENSCHAPPEN | CEWELD® Nicro 625 is a solid drawn wire that is cleaned in a very special way to obtain cleaner and higher quality welds with a bright seam and excellent ductility. Long term use at working temperatures between 600°C and 800°C should be avoided. | | | | | | | | | | | | | | | | |
| CLASSIFICATIE | <table border="0"> <tr> <td>AWS</td> <td>A 5.14: ERNiCrMo-3</td> </tr> <tr> <td>EN ISO</td> <td>18274: S Ni 6625 (NiCr22Mo9Nb)</td> </tr> <tr> <td>W.Nr.</td> <td>2.4831</td> </tr> <tr> <td>F-nr</td> <td>43</td> </tr> <tr> <td>FM</td> <td>6</td> </tr> </table> | AWS | A 5.14: ERNiCrMo-3 | EN ISO | 18274: S Ni 6625 (NiCr22Mo9Nb) | W.Nr. | 2.4831 | F-nr | 43 | FM | 6 | | | | | | |
| AWS | A 5.14: ERNiCrMo-3 | | | | | | | | | | | | | | | | |
| EN ISO | 18274: S Ni 6625 (NiCr22Mo9Nb) | | | | | | | | | | | | | | | | |
| W.Nr. | 2.4831 | | | | | | | | | | | | | | | | |
| F-nr | 43 | | | | | | | | | | | | | | | | |
| FM | 6 | | | | | | | | | | | | | | | | |
| GESCHIKT VOOR | <p>Ni 6625 / NiCr22Mo9Nb / 2.4831 W.Nr: 1.4529, 1.4539, 1.4547, 1.4876, 1.4958, 1.5656, 2.4660, 2.4816, 2.4856, 2.4858,</p> <p>X1CrNiMoCuN20-18-7 - X10NiCrAlTi32-20 - X5NiCrAlTi31-20 - NiCr15Fe - NiCr22Mo9Nb - NiCr21Mo - X1NiCrMoCuN25 20 6 - X1NiCrMoCuN25 20 5 - NiCr21Mo - 8XNi9</p> <p>ASTM: A 533 Gr1 UNS: S31254 - N08800 - N08810 - N06600 - N06625 - N08825 - N08926 - N08020 Alloy 254 SMO - Alloy 800 - Alloy 800H - Alloy 600 - Alloy 625 - Alloy 825 - Sanicro 28 - AL6XN</p> | | | | | | | | | | | | | | | | |
| GOEDKEURINGEN | TÜV: 12400.00 | | | | | | | | | | | | | | | | |
| LASPOSITIES |  | | | | | | | | | | | | | | | | |
| TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%) | <table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Fe</th> <th>Nb+Ta</th> </tr> </thead> <tbody> <tr> <td>0.08</td> <td>0.07</td> <td>0.4</td> <td>21</td> <td>65</td> <td>9</td> <td>0.5</td> <td>3.8</td> </tr> </tbody> </table> | C | Si | Mn | Cr | Ni | Mo | Fe | Nb+Ta | 0.08 | 0.07 | 0.4 | 21 | 65 | 9 | 0.5 | 3.8 |
| C | Si | Mn | Cr | Ni | Mo | Fe | Nb+Ta | | | | | | | | | | |
| 0.08 | 0.07 | 0.4 | 21 | 65 | 9 | 0.5 | 3.8 | | | | | | | | | | |
| MECHANISCHE WAARDEN | <table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{p0,2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th>RT</th> <th>-196°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>460</td> <td>750</td> <td>32</td> <td>110</td> <td>70</td> <td>HRc</td> </tr> </tbody> </table> | Heat Treatment | R _{p0,2} (MPa) | R _m (MPa) | A ₅ (%) | Impact Energy (J) ISO-V | | Hardness | RT | -196°C | As Welded | 460 | 750 | 32 | 110 | 70 | HRc |
| Heat Treatment | R _{p0,2} (MPa) | | | | | R _m (MPa) | A ₅ (%) | | Impact Energy (J) ISO-V | | Hardness | | | | | | |
| | | RT | -196°C | | | | | | | | | | | | | | |
| As Welded | 460 | 750 | 32 | 110 | 70 | HRc | | | | | | | | | | | |
| HERDROGEN | Not required | | | | | | | | | | | | | | | | |
| GAS ACC. EN ISO 14175 | I1 | | | | | | | | | | | | | | | | |



CEWELD NiCro 625 Tig

| | | | |
|-------------------------------|-----------|---------|---------------|
| NICRO 625 TIG 1,0 X 1000MM | Packaging | KG/unit | EanCode |
| | Tube | 5 | 8720663418852 |
| NICRO 625 TIG 1,2 X 1000MM | Packaging | KG/unit | EanCode |
| | Tube | 5 | 8720663418869 |
| NICRO 625 TIG 1,6 X 1000MM | Packaging | KG/unit | EanCode |
| | Tube | 5 | 8720663418876 |
| NICRO 625 TIG 1,6 X 914MM | Packaging | KG/unit | EanCode |
| | Tube | 4,54 | 8720663418883 |
| NICRO 625 TIG 2,0 X 1000MM | Packaging | KG/unit | EanCode |
| | Tube | 5 | 8720663418890 |
| NICRO 625 TIG 2,0 X 914MM | Packaging | KG/unit | EanCode |
| | Tube | 4,54 | 8720663418906 |
| NICRO 625 TIG 2,4 X 1000MM | Packaging | KG/unit | EanCode |
| | Tube | 5 | 8720663418913 |
| NICRO 625 TIG 2,4 X 914MM | Packaging | KG/unit | EanCode |
| | Tube | 4,54 | 8720663419040 |
| NICRO 625 TIG 3,2 X 1000MM | Packaging | KG/unit | EanCode |
| | Tube | 5 | 8720663418920 |
| NICRO 625 TIG 3,2 X 914MM | Packaging | KG/unit | EanCode |
| | Tube | 4,54 | 8720663418937 |