



CEWELD 904L

TYPE	Solid stainless steel austenitic filler metal with excellent corrosion resistance																
TOEPASSINGEN	Tanks and process vessels, Piping systems, agitators, rotors, cast pumps and valves for use in the fertilizer, phosphoric, sulphuric and acetic acid plants																
EIGENSCHAPPEN	The CEWELD® 904L is used for welding materials of similar chemical composition which are used for fabrication of equipment and vessels for handling of sulfuric acid and many chloride containing media. This filler metal may also find applications for joining Type 317L material where improved corrosion resistance in specific media is needed. In order to reduce the propensity for fissuring and hot cracking, the low melting constituents such as carbon, silicon, and phosphorus are controlled to lower levels in this alloy.																
CLASSIFICATIE	<table border="0"> <tr> <td>AWS</td> <td>A 5.9: ER385</td> </tr> <tr> <td>EN ISO</td> <td>14343-A: G 20 25 5 Cu L</td> </tr> <tr> <td>W.Nr.</td> <td>1.4539</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>5</td> </tr> </table>	AWS	A 5.9: ER385	EN ISO	14343-A: G 20 25 5 Cu L	W.Nr.	1.4539	F-nr	6	FM	5						
AWS	A 5.9: ER385																
EN ISO	14343-A: G 20 25 5 Cu L																
W.Nr.	1.4539																
F-nr	6																
FM	5																
GESCHIKT VOOR	<p>1.4465, 1.4500, 1.4505, 1.4506, 1.4519, 1.4531, 1.4536, 1.4537, 1.4538, 1.4539, 1.4573, 1.4585, 1.4586, 1.4539, 1.4537, 1.4519, 1.4505</p> <p>X1CrNiMoN25-25-2, X1NiCrMoCu 25-20-5, X1CrNiMoCuN 25-25-5, X2NiCrMoCuN25-20-5, X2NiCrMoCuN20-18, X4NiCrMoCuNb 20-18-2, X5NiCrMoCuTi20-18, X5NiCrMoCuNb22-18</p> <p>ASTM A182, UNS N08904, S31726 Uranus B6, 904L, Z2NCDU25-20,</p>																
GOEDKEURINGEN	CE																
LASPOSITIES																	
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>0.019</td> <td>0.35</td> <td>2</td> <td>20.5</td> <td>25</td> <td>4.6</td> <td>1.6</td> </tr> </tbody> </table>	C	Si	Mn	Cr	Ni	Mo	Cu	0.019	0.35	2	20.5	25	4.6	1.6		
C	Si	Mn	Cr	Ni	Mo	Cu											
0.019	0.35	2	20.5	25	4.6	1.6											
MECHANISCHE WAARDEN	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0.2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">RT</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>380</td> <td>560</td> <td>35</td> <td colspan="2">70</td> <td>HRC</td> </tr> </tbody> </table>	Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	RT		As Welded	380	560	35	70		HRC
Heat Treatment	R _{P0.2} (MPa)					R _m (MPa)	A ₅ (%)		Impact Energy (J) ISO-V		Hardness						
		RT															
As Welded	380	560	35	70		HRC											
HERDROGEN	Not required																
GAS ACC. EN ISO 14175	M13, M12																



CEWELD 904L

904L 0,8MM

Packaging	KG/unit	EanCode
BS-300	15	8720663415400

904L 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663415417

904L 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663415424