



CEWELD 347Si

TYPE Solid Niobium stabilized stainless steel welding wire

TOEPASSINGEN For welding stainless austenitic steels that are exposed to working temperatures up to 400°C.

EIGENSCHAPPEN The weld deposit is scale-resistant up to approx. 800°C in normal atmosphere and oxidizing gases. The weld deposit is capable of taking a high polish. Structure: Austenite with delta ferrite

CLASSIFICATIE

AWS	A 5.9: ER347Si
EN ISO	14343-A: G 19 9 Nb Si
W.Nr.	1.4551
F-nr	6
FM	5

GESCHIKT VOOR **ISO 15608: 8.1 / TÜV Groupe 29 (+22+21) / E347, 19 9 Nb, 1.4551**
 1.4541, 1.4550, 1.4552 1.4319, 1.4306, 1.4306, 1.4301, 1.4303, 1.4308, 1.4310, 1.4312, (1.4000, 1.4001, 1.4002, 1.4003, 1.4006)
 X 6 NiTi 18 10, X 6CrNiNb 18 10, G-X 5CrNiNb 18 9, X 5CrNi 18 7, X 2CrNi 19 11, G-X 2CrNi 18 9, X 5CrNi 18 10,
 X 5CrNi 18 12 G-X, 6CrNi 18 9, X 12CrNi 17 7, G-X 10CrNi 18 8
 AISI: 321, 347

GOEDKEURINGEN TÜV: 12393.00, CE

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	Cr	Ni
0.04	0.7	1.9	19.5	10

MECHANISCHE WAARDEN

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
				RT	-196°C	
As Welded	420	590	35	80	45	HRC

HERDROGEN Not required

GAS ACC. EN ISO 14175 M13, M12