



CEWELD AA B890SR

TYPE	Medium alloyed, high-strength flux-cored wire for M21 shielding gas																													
TOEPASSINGEN	Crane-, plant-, craft- and steel construction, pipe work, foundries.																													
EIGENSCHAPPEN	Remarkable crack resistant weld metal in combination with very low hydrogen content. Therefore, suitable for the economic processing of high-strength and low temperature fine-grained structural steels. Excellent welding properties in short and spray arc. Excellent gap bridging for root welds. High deposition rate and no intermediate cleaning required with very low spatter loss. Weld metal is heat treatable.																													
CLASSIFICATIE	AWS	A 5.36: E130T5-M21A4-K4-H4																												
	EN ISO	18276-A: T 89 0 Z B M21 3 H5																												
	F-nr	6																												
	FM	4																												
GESCHIKT VOOR	Reh ≤ 890 MPa ISO 15608: 5.1 1.7220, 1.7225, 1.7228, 1.7336 13 CrMoSi5-5, 13CrMo4-5, 25CrMo4, 26 CrMo4-2, 34CrMo4, 42CrMo4, 50CrMoSi5-5, 28NiCrMo44, (S690Q-S890Q, S690QL-S890QL) ASTM A 829M, A387, SAE 4135-37, 4140-45, 4150 UNS G41350-70, G41400-50, G41500 40CD4, 42CD4 / 40CD4u, 42CD4u Firmodur 7225, 7227., Thyssen TK 7225, 7227																													
GOEDKEURINGEN	CE																													
LASPOSITIES																														
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> </tr> </thead> <tbody> <tr> <td>0.05</td> <td>0.5</td> <td>1.5</td> <td>0.015</td> <td>0.015</td> <td>0.5</td> <td>2.2</td> <td>0.5</td> </tr> </tbody> </table>							C	Si	Mn	P	S	Cr	Ni	Mo	0.05	0.5	1.5	0.015	0.015	0.5	2.2	0.5							
C	Si	Mn	P	S	Cr	Ni	Mo																							
0.05	0.5	1.5	0.015	0.015	0.5	2.2	0.5																							
MECHANISCHE WAARDEN	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0,2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">RT</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>920</td> <td>1010</td> <td>17</td> <td colspan="2">75</td> <td>HRc</td> </tr> <tr> <td>620°C±15°C 1h</td> <td>710</td> <td>910</td> <td>18</td> <td colspan="2">55</td> <td>HRc</td> </tr> </tbody> </table>							Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	RT		As Welded	920	1010	17	75		HRc	620°C±15°C 1h	710	910	18	55		HRc
Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness																								
				RT																										
As Welded	920	1010	17	75		HRc																								
620°C±15°C 1h	710	910	18	55		HRc																								
HERDROGEN	Not required																													
GAS ACC. EN ISO 14175	M21																													